



Accura[®] CeraMAX[™]

Specialty Class

Composite material for manufacturing stable, high-stiffness parts

Post-Cured Material

MEASUREMENT	CONDITION	METRIC	U.S.
Tensile Strength (MPa/PSI)	ASTM D 638	78-87	11300-12600
Tensile Modulus (MPa/KSI)	ASTM D 638	9460-9680	1370-1400
Elongation at Break (%)	ASTM D 638	1 - 1.5	1 - 1.5
Flexural Strength (MPa/PSI)	ASTM D 790	137-145	19.9-21.0
Flexural Modulus (MPa/KSI)	ASTM D 790	8270-8370	1200-1210
Impact Strength (J/m /Ft-lbs/in)	ASTM D 256	14.5-17.9	0.27-0.34
Heat Deflection Temperature	ASTM D 648		
UV Postcure Only	@ 66 PSI	148 °C	298 °F
UV Postcure Only	@ 264 PSI	95 °C	203 °F
UV + thermal postcure (2hr @ 120 °C)	@ 66 PSI	220 °C	428 °F
UV + thermal postcure (2hr @ 120 °C)	@ 264 PSI	97 °C	207 °F
Coefficient of Thermal Expansion (CTE)	ASTM E 831-93		
	25-57 °C	31.1	17.3
	70-200 °C	87.4	45.6
Glass Transition (Tg)	DMA, E"		
UV Postcure Only		82 °C	180 °F
120 °C thermal postcure		94 °C	201 °F
Hardness, Shore D		89	89

Features

- Highest stiffness available
- Heat and abrasion resistant
- Excellent chemical resistance
- Great for windtunnel models, jigs and fixtures

Liquid Material

MEASUREMENT	CONDITION	VALUE
Viscosity	@ 30 °C (86 °F)	1500-2000 cps
Penetration Depth (Dp)		5.7 mils
Critical Exposure (Ec)		7.2 mJ/cm ²
Color		White
Solid Density	@ 25 °C (77 °F)	1.62 g/cm ³
Liquid Density	@ 25 °C (77 °F)	1.59 g/cm ³



www.3dsystems.com

UK

Tel: +44 1442 282 600
info@3dsystems-europe.com

USA

Tel: +1 803.326.3900
moreinfo@3dsystems.com

Germany, Scandinavia, Eastern Europe, Middle East

Tel: +49 6151 357 0
info@3dsystems-europe.com

Asia-Pacific

Melbourne Tel: +61 3 9819 4422
 Sydney Tel: +61 2 9516 5571
3dprinters.asiapac@3dsystems.com

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2017 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. CeraMAX is a trademark, the 3D logo and Accura are registered trademarks of 3D Systems, Inc.